

Synthesis and Characterization of Silver Nanoparticles from *Ipomoea Cairica L.* Leaf Extract and their Antibacterial Assay

Harshitha H S¹, Navyashree H T²

¹Student, Department of Botany, Bharathi College PG and Research Centre, Bharathi Nagar, K.M.Doddi, India

²Assistant Professor, Bharathi College PG and Research Centre, Bharathi Nagar, K.M.Doddi, India

Abstract: Nanoparticles is the fundamental building blocks of nanotechnology. Green synthesis of nanoparticles is an important and beneficial way without side effects caused by synthetic antibiotic and chemicals. The green method is easy efficient and eco-friendly compared to chemical mediated method. The present study is focused on the synthesis of silver nanoparticles using *Ipomoea* leaf extract and its antibacterial activity. The presence of AgNPs was confirmed by color change from light color to dark brown color and then by UV-Vis spectroscopy, SEM analysis and XRD-analysis. The antibacterial activity evaluated against *E.coli* and *S.aureus*.

Keywords: Green synthesis, Silver nanoparticles, *Ipomoea*

1. Introduction

Nanotechnology is the synthesis of nanosilver particles. [S.kaviya et al., 2011]. Nanotechnology is a field of science which deals with production, manipulation and use of nanomaterials ranging in size from 1-100nm. Nanomaterials have novel and enhanced useful characteristics due to their size, distribution and morphology in comparison to larger particles. [Kero jemal et al., 2017]. Nanotechnology can play significant role in drug therapy. Nanoparticles are synthesized by green method have application in bactericidal, wound healing, medicinal and electronics.[Somanath vibute et al., 2014]. *Ipomea cairica* is an evergreen, herbacious, perrineal climbing plant, Producing slender stems upto 5 meters. This vining perrinial has palmate leaves & leaves. Showy white to lavender flowers. The entire plant is used for treating external infections, eye troubles, body rashes, purigative. Plant contains steroids & terpenes. It has an antibiotic property.



Figure 1: *Ipomoea cairica*.L.

The aim of this work is to use *Ipomoea cairica*.L leaf extract as a low cost and ecofriendly approach to the green synthesis of silver Nanoparticles. My work upon nanoparticle has been characterized by UV-spectroscopy, SEM and XRD-Analysis.

2. Materials and Methods

a) Preparation of leaf extract

Fresh and young green leaves were collected. 20gms of each leaf sample were washed thoroughly with double distilled water (DDW). Then it is cut into small pieces. The finely cut pieces were placed in a 500ml Erlenmeyer flask containing 100ml of sterile DDW. After that the mixture was boiled for 5 minutes and filtered through whatman filter no.1 (C. Udayasoorian et al., 2011).

b) Synthesis of silver nanoparticles

Silver nitrate was used as a precursor in synthesis of silver nanoparticles . 5ml of leaf extract was added to 100ml of 1mmAgNo3(99.99%) aqueous solution in conical flask of 250ml content at room temperature. The flask were thereafter put in shaker (150ml) at 30 degree c and reaction was carried out for a period of 48hrs.

Antibacterial Activity:

Since silver and its salts exhibit strong antibacterial activity, this property was evaluated for the Ag-nano particles prepared by using *Ipomoea* leaf extract.

Analysis Method:

UV-Visible Spectroscopy

The bio reduction of Ag⁺ in the solvent extract was monitored by evaluation of the suspension(2 ml) before incubation and after incubation of 48 hours under dark condition , the aliquots were measured for the UV-Visible spectra by scanning in the region from 200-800 nm (Jyothi et al in 2016).

SEM Analysis

SEM Analysis was undertaken to know the size & shape of the silver nanoparticles biosynthesized using the plant leaf extract of *I.cairica* . The analysis was done using Noran system 7, S-3400 N model.

XRD-Analysis

The sample was drop-coated onto copper plate by just dropping a small amount of sample on the plate frequently allowed to dry & finally thick coat of sample was prepared . the XRD measurements was performed on a Rigako model with step size 0.02 & an angle of 60⁰-70⁰

The particle size of the prepared samples were determined by using Scherrer's equation as follows

$$D = \frac{k\lambda}{\beta \cos\theta}$$

where D is the crystal size , λ is the wave length of x-ray, θ is the Bragg's angle in radians and β is the full width at half maximum of the peak in radians . K is constant.

3. Results and Discussion

Observation

After 48 hrs, distinct change in the colour of experimental sample was observed. The colour of experimental sample turned from light green to dark brown colour. The brown colour confirms that the colour change is due to reduction of silver ion which indicates the formation of Ag nanoparticles.



Figure 2: A- Ipomoea leaf extract
 B- Ipomoea AgNPs solution

UV –vis Spectroscopy:

The conformation, formation & stability of synthesised silver nano particles was confirmed by uv-vis spectrum. 2ml of synthesised AgNPs solution of both Basella & Ipomoea were observed in before & after the incubation & the UV ranges between 200 -800nm. Before incubation, the synthesized AgNPs shows peak at 430nm of Ipomoea respectively. After the incubation period of 48hrs the synthesized AgNPs showed broad surface Plasmon resonance at 434nm of Ipomoea.




Figure 3: Spectra of Ipomoea AgNPs before incubation




Figure 4: Spectra of Ipomoea AgNPs after incubation

SEM Analysis

The SEM images show the AgNPs synthesized from Basella extract which is further confirms the presence of AgNPs. The shape of the AgNPs in Ipomoea extract was spherical & the size of AgNPs is 5.8mm as confirmed by SEM images.




Figure 5: SEM image of Ipomoea cairica AgNPs

XRD Analysis

X-ray Diffraction studies of two samples show different diffraction peaks. Ipomoea plant extract shows four different diffraction peaks at 27.71⁰, 32.17⁰, 38.25⁰ & 46.12⁰ . 2θ values & crystalline planes of Ag sample. The average size of the AgNps formed in bioreduction process is determined by using $D = \frac{k\lambda}{\beta \cos\theta}$ & it is estimated that average size if Ipomoea 231.95, 202.02, 125.22 & 220.28 shows the XRD pattern of the silver nano particle formed in our experiment.




Figure 6: XRD image of Ipomoea cairica AgNPs

A table shows XRD result of Ipomoea cairica silver nano particle


d-spacing	2-theta	HKL	Average size
3.21	27.71	0 1 2	231.95
2.77	32.17	1 1 0	202.02
2.35	38.25	2 1 0	125.22
1.96	46.21	0 0 1	220.28

Anti-Bacterial Analysis:

For *Ipomoea cairica* the zone of inhibition was found to be 1.0mm for *E.coli* ,0.8 mm for *S.aureus*.

Antibacterial Zone Formation:

Species	Basella (zone of inhibition)
E.coli	1.0
S.aureus	0.8



Escherichia coli



Staphylococcus aureus

Figure 6: Antibacterial activity of AgNPs of *Ipomoea cairica* against to selected bacterial culture by disc diffusion method

A – AgNPs solution of *Ipomoea cairica*,
 B-Positive control (Ampicilin),
 C-Negative control (water)

4. Conclusion

In the present study demonstrated that the aqueous extract of *Ipomoea cairica* leaves showed excellent antimicrobial activity. Synthesised AgNPs from the plant extracts are characterized using UV-Vis spectroscopy, SEM analysis and XRD-analysis. By this we can study the size and shape of the synthesized nanoparticle.

References

[1] Charushella Ramteke et. al., (2012). Synthesis of silver Nanoparticle from the aqueous extract of leaves of *Ocimum sanctum* for enhanced antibacterial activity, vol-3, Pp no-7.
 [2] Sreejamol, p., et,al.,(2014). Biosynthesis of silver nanoparticles from unripe *carica papaya* fruit extract and its antibacterial activity. Vol -4(3), Pp no-304-307.
 [3] A.A.Haleekhan et,al.,(2015). Synthesis of nanoparticles from plant extracts vol-2(3). Pp no-195-203.

[4] Akl M. Awwad and Naida M. Saleem.(2012). Green synthesis of silver nanoparticles by mulberry leaves extract. Vol -2(4). Pp no-(125-128).
 [5] Anandalakshmi k and Venugobal et.al.,(2017). Green synthesis and charectarization of silver Nanoparticles using *Vitex negundo* leaf extract and its Antibacterial activity. Vol-7, Pp no-218-225.
 [6] Ashish kumar gupta and Deepak Ganjewala(2015). Synthesis of silver nanoparticles from *Cymbopogon flexuosus* leaves extract and their antibacterial properties. Vol -1.Pp no-(225-230).
 [7] Fatma aly Farghaly & Nivien allam Nafaday. Green synthesis of silver nanoparticles using leaf extract of *rosmarinus Officinalis* and its effect on tomato and Wheat plants. Vol -7. Pp no-(277-287).
 [8] G.Mahendran and B.D. Ranjitha kumara(2016). Biological activities if silver nanoparticles from *Nathapodytes nimmoniana*(Graham) Mabb. Fruit extracts. Vol-5, Pp no-(207-218).
 [9] J.J.Antony,et,al.,(2013). Antimicrobial activity of *leucas aspera* engineered silver nanoparticles against *Aeromonas hydrophilla* in infected *Catla Catla*. Pp no-20-24.
 [10] Jyothi V. Vastrad and Giridhar Goudar(2016). Green synthesis and charectarization of silver nanoparticles using leaf extract of *Tridax procumbance* , vol-32(3).Pp no 1525-1530.
 [11] Kaviya S,et. al.,(2011). Green synthesis of silver Nanoparticles using *Polyalthia longifolia* leaf extract along with D-sorbital and study of antibacterial activity, vol -2, Pp no-5.
 [12] Kero jemalet,al.,(2017). Synthesis, characterization, and evaluation of the Antibacterial Activity of *Allophylus serratus* leaf and leaf derived callus extracts mediated Silver nanoparticles, vol-2017.
 [13] M.prathap et,al.,(2014). Antibacterial activities of silver nanoparticles synthesized from plant leaf extract of *abutilon indicum*(l).sweet. Vol -4,Pp no-106(1-6).
 [14] P.Kathireswari et. al., (2014). Green synthesis of silver nano particle using *vitex negundo* ans its antimicrobial activity against human pathogens, vol-3, Pp no-614-621.
 [15] PratapaRudra Manthur Padigya,et,al.,(2014). Green synthesis of silver Nanoparticles using *Canna indica* leaf extract and its characterization,vol-6, Pp no-2271-2276.
 [16] Priti Ranjan et,al.,(2013). Green synthesis and charectarization of silver nanoparticles from *Nigella sativa* and its application against UTI causing Bacteria. Vol-2 , Pp no-45-49.
 [17] Reenal M and Iruthaya selvam S. Green synthesis and Antibacterial activity of silver nanoparticles using *Oryza sativa* husk extract. Vol-4(5), Pp no-68-72.
 [18] S.R.Sivakumar et ,al.,(2017). Antioxidant , Antimicrobial and Sewage treatment of synthesized silver nanoparticles from leaf extract of *Hygrophila auriculata*(schumsch) heine. Vol -4(08). Pp no-(2350-2361).
 [19] Somanath vibhute,et,al.,(2014). Synthesis of silver nanoparticles from *moringa oliefera*: Formulation and evaluation against...vol-4,Pp no-1581-1587.
 [20] Udayasoorian C . et. al., (2011). Extracellular synthesis of silver nanoparticles using leaf extract of *Cassia auriculata* , vol-6(1), Pp no- 279-283